



BERBERICH PAPIER

80 g/m²

Kwidzyn

Rey Office (FSC-zertifiziert)

Substance	Flächenbezogene Masse	ISO 536	<i>g / m²</i>	80 ± 2
Thickness	Bogenhöhe / Dicke	ISO 534	<i>µm</i>	108 ± 3
Bulk	Volumen			1,35
Stiffness	Steifigkeit	ISO 2493	<i>m/N</i>	114 +/- 10 MD 54 +/- 5 CD
Smoothness	Glätte	ISO 8791	<i>Bendtsen, ml/min</i>	180 ± 50
Whiteness	Weisse	ISO 11475	<i>CIE</i>	161 ± 2
Opacity	Opazität	ISO 2471	<i>%</i>	94 +/- 2

100% ECF PULP

ISO 9001:2000 : Quality control / Contrôle Qualité

ISO 14001 : Environmental protection / Protection de l'Environnement

OHSAS 18001 : Health & Safety

This document is not contractual and can be modified without notice - Ce document n'est pas contractuel et peut être modifié sans préavis



PL/011/001



The mark of
responsible forestry